

SCHEDA TECNICO-COMMERCIALE

Commercial - Technical Data

Articolo / Article:

800 ALABAMA

Composizione / Composition:

91% POLYESTER

9% ELASTANE

Scopri di più.

Find out more.

Peso / Weight (+/- 5 %): 260 g/m²

Peso / Weight (+/- 5 %): 395 g/m lin.

Altezza / Width (+/- 2%): 152 cm

Pezza / Piece: 50 m

Stabilità Dimensionale - Lavaggio 40° C

Dimensional Stability - Washing 40° C

BS EN ISO 6330 @40°C - flat dry

altezza / width: max -3%

lunghezza / length: max -3%

Stabilità Dimensionale - Vapore

Dimensional Stability - Steam

altezza / width: max -3%

lunghezza / length: max -3%

Resistenza al Pilling/Resistance to Pilling

NU Martindale - ISO 12945-2 7000 rotations

su lana: 4/5

on wool:

Abrasione 12kPa/Abrasion 12kPa

NU Martindale - ISO 12945-2

su lana: >40000

on wool:

Allungamento al Dinamometro (+/- 15%)

Stretch to Dynamometer (+/- 15%)

INSTRON 3343 - load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm.

Tinto / Plain dyed

altezza / width: 90%

(min 77% - max 104%)

lunghezza / length: 60%

(min 51% - max 69%)

Allungamento Manuale (+/- 15 %)

Hand Elongation

altezza / width: 95%

(min 81% - max 109%)

lunghezza / length: 65%

(min 56% - max 74%)

Simboli di manutenzione:

Care labelling codes:

Test di infiammabilità / Flammability test :

BS 5852-1:1979 - Smouldering Cigarette Test on upholstered furniture (Ref. Schedule 4 Part I): PASS (NON fire- retardant polyurethane foam with a density of 21 kg/m³) | EN 1021-1:2014 - Smouldering Cigarette Test on upholstered furniture: PASS (fire-retardant polyurethane foam with a density of 35 kg/m³) | TB 117:2013 - Smouldering Cigarette Test on upholstered furniture: PASS (NON fire-retardant polyurethane foam with a density of 28 kg/m³) | BS 5852-1:1979 - Match Test on upholstered furniture (Ref. Schedule 5 Part II – “stretch covers”): PASS (fire- retardant polyurethane foam with a density of 25 kg/m³) | UNI 9175:1987+UNI 9175 FA-1:1994 - Reaction to fire of upholstered furnitures by applying a small flame: PASS - CLASS1.IM

Certificati:

Certifications:

Note / Notes:

Tessuto con trattamento superficiale. L'aspetto potrebbe subire leggere variazioni.

As this fabric is surface treated, the look could be subject to slight variations.

Raccomandiamo di testare ogni bagno prima di qualsiasi trattamento o applicazione che non sia taglio e cucito.

We recommend testing each dyebath before any treatment or application other than cutting and sewing.

Il produttore, al fine di migliorare il prodotto, si riserva di apportare qualunque modifica in qualsiasi momento.

To improve our products, we reserve the right to modify these, as and when necessary.

Annulla e sostituisce la precedente del Febbraio 2025 / Replaces the previous data sheet of February 2025